

Technical Information

Acrylic enamel of a special purpose. Forms a durable coating with a high content of metallized pigment. Highly adhesive. Has a high spreading capacity. Highly resistant to abrasive impacts of sand, flying stones, corrosive impact of water and road reagents. Resistant to weathering and temperature changes. Does not fade in the sun.

Designed for painting and restoring paint coat of rims of cars, buses, motorcycles and other vehicles.

In order to achieve maximum gloss and optimum protection apply a colorless [acrylic lacquer Biodur](#) as a finishing coat 30 min after applying the final coat of enamel.

Quality & properties

One aerosol is enough for 4 discs.

Does not burn out in the sun.

Forms an ultra-durable coating with a "metallic" effect

Physical & chemical data

Content: 500 ml

Base: acryl resin

Color : according to the assortment

Paint effect : gloss

Coverage area: 4 discs

Drying time to degree 3 at 20 (±2)°C: no more 30 minutes

Density at 20 (±2)°C: 0,75-1,20 g/cm³
(depending on enamel color)

Coating adhesion to metal : no more 2 score

How to use

Before use, carefully read the directions on the packaging and act accordingly.

The surface should be clean, dry and free of grease. Remove loose old lacquer and rust and sand the surface.

The aerosol should have room temperature. Best processing temperature 15 to 30°C.

Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimetre.

Apply the enamel in several thin layers. Before applying the next layer, again shake the aerosol.

After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.

Conditions of storage and transportation of products: Products are transported by any ground mode of transport in compliance with the rules of cargo transportation. Products in packaged form must be stored in premises that protect products from chemical influences and mechanical damage at a temperature not lower than minus 20C and not higher than plus 40C.

Stability during storage: 5 years from the date of manufacture. The date of manufacture is indicated on the bottom of the aerosol.

Regulatory and legislative information

Regulation (EC) No. 1907/2006 of the European Parliament and of the Council of 18th December 2006 concerning the Registration, Evaluation, Authorisation and Restriction of Chemicals (REACH), establishing the European Chemicals Agency, amending Directive 1999/45/EC and repealing Council Regulation (EEC) No. 793/93 and Commission Regulation (EC) No. 1488/94 as well as Council Directive 76/769/EEC and Commission Directives 91/155/EEC, 93/67/EEC, 93/105/EC and 2000/21/EC, as amended. REGULATION (EC) No. 1272/2008 OF THE EUROPEAN PARLIAMENT AND OF THE COUNCIL as amended. Commission Regulation (EU) 2020/878 of 18 June 2020 amending Annex II to Regulation (EC) No 1907/2006 of the European Parliament and of the Council concerning the Registration, Evaluation,

Authorisation and Restriction of Chemicals (REACH).

