

BIODUR Sp. z o. o.

Krakow, Halicka str. 9, 31-036, Poland
Tel: +4812 376 6552
info@biodur.pl
www.biodur.pl

TECHNICAL DATA SHEET

ACRYLIC PRIMER**Product description**

Primer universal for preparation for painting metal, wood, glass, stone, brick and some types of plastic surfaces. Fills in scratches and cavities. Makes strong protective coat ready for polishing 30 min after application. Primered surface is resistant to mechanical and weather impact. Compatible with all paint systems.

Product characteristics

Fast drying
Excellent coverage and filling property
Anti-corrosion
Easy to sand, both wet and dry

Physical and Chemical Characteristics

Contents	500 ml
Base	Acrylic resin
Gloss	Matt
Coverage	1,25 to 1,75 m ²
Dust dry	After 10 to 30 minutes
Tack free	After 3 to 4 hours
Hardened/re-sprayable	After 24 hours
Heat resistant	To 110°C

Usage

Before use, carefully read the instructions on the packaging and act accordingly.

Pre Treatment

Remove loose old paint and rust and sand the surface. Clean, dry and degrease the surface.

Treatment

The surface should be clean, dry and free of grease. The aerosol should have temperature between +15 to +30°C. Best processing temperature +15 to +25°C. Before use, shake the aerosol for 2 minutes and make a test spray. Keep the distance to the surface that has to be treated approximately 25 to 30 centimetre.

Apply the primer in several thin layers. Before applying the next layer, again shake the aerosol.

After use, clean the valve (turn aerosol upside down and press the actuator till you see clear spray).

The drying time depends on the ambient temperature, the humidity of the air and thickness of applied coating.